

Dkt. No. 25363A

RECEIVED
CENTRAL FAX CENTER
FEB 5 - 2008

CLAIM AMENDMENTS

1. (previously presented) A liner/insulator comprising:
 - a) a first layer of wet processed mat;
 - b) a second layer of wet processed mat directly bonded to said first layer;wherein said first and second layers comprise thermoplastic polymer staple fibers and thermoplastic bicomponent fibers of different fiber formulations.
2. (original) The liner/insulator of claim 1, further comprising a third layer of wet processed mat comprising thermoplastic polymer staple fibers and thermoplastic bicomponent fibers.
3. (original) The liner/insulator of claim 2, wherein said thermoplastic staple fibers and said thermoplastic bicomponent fibers are selected from a group of materials consisting of polyester, polyethylene, polypropylene, polyethylene terephthalate and any mixtures and/or copolymers thereof.
4. (original) The liner insulator of claim 2, wherein said first, second and third layers are bonded together.
5. (original) The liner/insulator of claim 4, wherein said layers are bonded together by heat and pressure.
6. (original) The liner/insulator of claim 1, wherein said first and said second layers are between about 0.05 to about 0.30 inches thick.
7. (original) The liner/insulator of claim 2, wherein said third layer is between about 0.05 to about 0.30 inches thick.
8. (original) The liner/insulator of claim 7, wherein said liner/insulator is between about 0.125 to about 1.5 inches thick.
9. (previously presented) The liner/insulator of claim 1, wherein said first layer is hydrophilic.

Dkt. No. 25363A

10. (previously presented) The liner/insulator of claim 1, wherein said first layer has a high heat resistance.

11. (previously presented) The liner/insulator of claim 1, wherein said second layer is hydrophobic.

12. (original) The liner/insulator of claim 2, wherein said third layer is sound absorbent.

13. (previously presented) A method of producing a wet processed liner/insulator comprising the steps of:

a) providing a first layer of wet processed mat;

b) providing a second layer of wet processed mat having a different fiber formulation than said first layer;

wherein said first and second layers comprise thermoplastic polymer staple fibers and thermoplastic bicomponent fibers;

c) applying sufficient heat and pressure to said first and second layers of mat to bond said first layer and said second layer directly together and form said liner/insulator.

14. (original) The method of claim 13, further comprising the step of providing a third layer of wet processed mat comprising thermoplastic polymer staple fibers and thermoplastic bicomponent fibers.

15. (original) The method of claim 14, wherein said thermoplastic staple fibers and said thermoplastic bicomponent fibers are selected from a group of materials consisting of polyester, polyethylene, polypropylene, polyethylene terephthalate and any mixtures and/or copolymers thereof.

16. (original) The method of claim 13, wherein said first and said second layers are between about 0.05 to about 0.30 inches thick.

Dkt. No. 25363A

17. (original) The method of claim 14, wherein said third layer is between about 0.05 to about 0.30 inches thick.
18. (original) The method of claim 13, wherein said liner/insulator is between about 0.125 to about 1.5 inches thick.
19. (previously presented) The method of claim 13, wherein said first layer is hydrophilic.
20. (previously presented) The method of claim 13, wherein said first layer has a high heat resistance.
21. (previously presented) The method of claim 13, wherein said second layer is hydrophobic.
22. (original) The method of claim 14, wherein said third layer is sound absorbent.
23. (original) The method of claim 13, wherein heat is applied to said first and said second layers at a temperature of about 250 degrees F to about 400 degrees F.
24. (currently amended) The liner/insulator of claim 1, wherein ~~the first and second layers have different fiber compositions~~ the first layer has a first fiber composition and the second layer has a second fiber composition, wherein the first fiber composition is different from the second fiber composition.
25. (currently amended) A liner/insulator comprising:
 - a) a first layer of wet processed mat;
 - b) a second, discrete layer of wet processed mat directly bonded to said first layer;
 - c) a third, discrete layer of wet processed mat directly bonded to said second layer;wherein said first, second, and third layers comprise thermoplastic polymer staple fibers and thermoplastic bicomponent fibers, which bicomponent fibers bond the fibers together within each individual layer of the mat.

Dkt. No. 25363A

26. (previously presented) A liner/insulator comprising:
- a) a first individual layer of wet processed mat having a first face;
 - b) a second individual layer of wet processed mat having a second face contacting said first face of said first layer;
- wherein said first and second individual layers comprise thermoplastic polymer staple fibers and thermoplastic bicomponent fibers of different fiber formulations.
27. (previously presented) A method of producing a wet processed liner/insulator comprising the steps of:
- a) wet processing thermoplastic polymer staple fibers and thermoplastic bicomponent fibers to form a first layer of wet processed mat having a first face;
 - b) wet processing thermoplastic polymer staple fibers and thermoplastic bicomponent fibers to form a second layer of wet processed mat having a different fiber formulation than said first layer, said second layer having a second face; and
 - c) applying sufficient heat and pressure to said first and second layers of mat to bond said first layer and said second layer directly together and form said liner/insulator.